

Technical Data Sheet

Product	Film/ Film and Film/Wiremesh Faced Plywood
Specification	2500x1250x18mm/21mm
Wood Species	Eucalyptus
Glue	WBP Phenol Glue to meet bonding EN314-2, Class 3; EN636-3.
Film	Smooth side 165gr/m² Phenol Film/Wiremesh: 240gr/m² Phenol film
Moisture Content	8-14%
Density	580kg/m³
Thickness Tolerance	0.5mm
Tolerance in Length and width	1.0mm
Bending Strength	long Grain: 35-45 N/mm² Cross: Grain: 45-55 N/mm²
Modulus of Elasticity In Bending	long Grain: > 6000 N/mm² Cross Grain: > 7000 N/mm²

